This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES:
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problems Mailbox.

3

(11) (A) No. 1 205 031

(45) ISSUED 860527

(52) CLASS 195-82 C.R. CL. 195-131; 260-219

(51) INT. CL. C12P 19/26, C08B 37/08

(19) (CA) CANADIAN PATENT (12)

- (54) Hyaluronic Acid Fractions Having Pharmaceutical Activity, and Processes for the Preparation Thereof

(21) APPLICATION No.

465,231

(22) FILED

841011

(30) PRIORITY DATE


Italy (49143-A/83) 831011 Italy (48979A/84) 841009

No. OF CLAIMS

8

Canadä

DISTRIBUTED BY THE PATENT OFFICE, OTTAWA. CCA-274 (11-82)



AVERAGE MOLECULAR WEIGHT OF HYALURONIC ACID

Manuel Applicant)

This invention relates to specific molecular weight fractions of hyaluronic acid (hereinafter referred to as "HA") which have therapeutic applications and which are non-inflammatory when utilized. One of the HA fractions of this invention is useful for facilitating wound healing, while the second HA fraction is useful for intraocular use to substitute for endobulbar fluids or for intraarticular injection for use in treating damaged bone joints. The HA fractions have further been found to be useful as vehicles for ophthalmic drugs providing formulations compatible with the corneal epithelium and enhancing the activity of ophthalmic drugs.

Hyaluronic acid is a naturally occurring heteropolysaccharide consisting of alternating residues of D-glucuronic acid and N-acetyl-D-glucosamine. HA is a linear polymer of high molecular weight, generally up to \ \8 to 13 million, and has been found in cell coats, the extracellular ground substance of connective tissues of vertebrates, in the synovial fluid in joints, in the endobulbar fluids of the eye, in human umbilical cord tissue, and in rooster combs.

Previous investigations on the use of HA are included in the work of Balazs, U.S. Patent 4,141,973, directed to afraction of HA useful for replacing endobulbar fluids, as well as other therapeutic applications. This patent, however, is specifically directed to an HA fraction having an average 750,000, and preferably molecular weight greater than . 1,200,000. Balazs specifically teaches greater than that fractions of HA having an average molecular weight of less than 750,000 are not therapeutically useful because of their inflammatory activity. These lower molecular weight fractions of HA are discarded by Balazs. However, this 90% of the total amount of results in discarding available HA obtainable from the source tissues, resulting in a use of only a small amount (10%) of the available HA.

10

20

30

to

As discussed above, previous investigations of HA, as exemplified by the Balazs patent, have been directed to utilizing high molecular weight fractions with an average molecular weight of greater than 750,000. The present applicant has isolated and characterized two new fractions of HA, one having a low molecular weight and another having a medium ranged average molecular weight, which are considered to be substantially pure as they are of a high degree of purity and do not have inflammatory activity. These new fractions of HA can be obtained from various connective tissues which contain extractable amounts of hyaluronic acid. The specific fractions of this facet of this invention are differentiated and separated according to molecular filtration techniques.

The first fraction isolated by the applicant has been named HYALASTINE, and has an average molecular weight of from \50,000 to \100,000. This HYALASTINE fraction has been determined to be suitable for therapeutic, veterinary and human use because of its wound healing activity. The second fraction isolated by the applicant has been labeled HYALECTIN, and has an average molecular weight of \500,000

\730,000. This HYALECTIN fraction is suitable for use

in ocular surgery as a substitute for endobulbar liquids and for veterinary and human therapy in traumatic and degenerative diseases of the joints.

HYALASTINE can be administered either as an intradermal injection or it can be applied as a topical agent for wound healing. HYALECTIN, on the other hand, is suitable for intraocular and intraarticular injection.

The present applicant has made intensive studies on the various fractions of HA and, in a significantly more precise way than previously accomplished, has specifically determined the therapeutically useful fractions of HA and the inflammatory and non-useful fractions of HA.

Contrary to the teachings of Balazs, the present applicant has discovered that lower molecular weight fractions of HA do indeed have useful pharmaceutical activity. Thus, according to the present invention, 80% of the HA obtainable from various sources is utilized. In particular, the present applicant has discovered one fraction of HA which is useful for stimulating wound healing, and a second fraction of HA which is useful for intraocular injections to substitute for the endobulbar liquids in the eye and for intraarticular injections as a treatment for damaged joints.

Thus by one aspect of this invention a process is provided for preparing a substantially pure, non-inflammatory, hyaluronic acid fraction comprising: dehydrating tissue containing an available amount of hyaluronic acid; subjecting the resulting dehydrated tissue to enzymatic digestion; subjecting the resulting mixture to molecular filtration to obtain a hyaluronic acid fraction having an average molecular weight of from | 50,000 to 100,000, from 250,000 to \ 350,000 or from -500,000 to 730,000.

30

By another aspect of this invention, a process is provided for preparing a substantially pure, non-inflammatory hyaluronic acid fraction comprising: dehydrating tissue available for extraction of hyaluronic acid; subjecting the resulting substance to enzymatic digestion; subjecting the resulting mixture to molecular filtration with a membrane having a molecular weight exclusion limit of 30,000 to exclude molecules having a molecular weight of greater than 30,000; collecting the mixture retained by the membrane; thereby obtaining a substantially pure, non-inflammatory first hyaluronic acid fraction product having an average molecular weight of from 250,000 to 350,000.

10

By a variant of this aspect of the invention, the first substantially pure, non-inflammatory hyaluronic acid fraction is subjected to further molecular ultra-filtration with a membrane having a molecular weight exclusion limit of 200,000 to exclude molecules having a molecular weight of greater than 200,000; the ultra-filtration is continued until the volume of the mixture being subjected to ultra-filtration is reduced to 10% of the initial volume; and the mixture which passes through the membrane is collected; thereby to obtain a second substantially pure, non-inflammatory hyaluronic fraction product having an average molecular weight of from 50,000 to 100,000.

20

By another variant thereof, the mixture retained on the membrane after the ultra-filtration with the membrane having a molecular weight exclusion limit of 200,000 (as described above) is collected thereby obtaining a third substantially pure non-inflammatory hyaluronic acid fraction product having an average molecular weight of from 500,000 to 730,000.

By other aspects of this invention a substantially pure, non-inflammatory hyaluronic acid fraction having an average molecular weight of between 30,000 and 730,000, or the potassium or sodium salt thereof

is provided, e.g. having an average molecular weight of between 250,000 and 350,000 or the potassium or sodium salt thereof, or having an average molecular weight of between 50,000 and 100,000 or the potassium or sodium salt thereof, or having an average molecular weight of between 500,000 and 730,000 or the potassium or sodium salt thereof, by the various processes described above.

As a result of the studies by the present applicant alluded to above, the present applicant has identified and investigated two specific characteristics of HA fractions, namely cell mobilization activity and intrinsic viscosity. The wound healing process in animals is facilitated by cellular mobilization, and particularly the mobilization of fibroblasts. On the other hand, cellular mobilization or proliferation activity (i.e., mytosis) is to be avoided in cases of surgery inside the ocular globe. This is particularly true in operations to correct retinal detachment where an increased rate of healing may cause harmful affects.

10

20

The intrinsic viscosity is also an important parameter to be considered in determining the utility of a fraction of HA. A fraction having a high intrinsic viscosity is useful for surgical uses, in the therapy of diseases of the joints of a traumatic and degenerative nature, and for replacing endobulbar liquids. On the other hand, high viscosity is an undesirable characteristic for fractions to be utilized as drugs for facilitating wound healing. In fact, fractions to be utilized in wound healing should have low viscosity so as to be more easily used in practical application.

The HYALASTINE fraction identified by the present applicant has been determined to have good mobilization or cell proliferation activity,

and low viscosity characteristics. Accordingly, HYALASTINE has the characteristics desirable for a material useful in promoting wound healing.

The same characteristics make the HYALASTINE fraction undesirable for use in intraocular or intraarticular injection treatments.

The HYALECTIN fraction identified by the applicant has been determined to have negligible cell mobilization or proliferation activity, while at the same time having high

viscosity. These characteristics, therefore, make the HYALECTIN fraction useful for intraocular and intraarticular injection treatments. But, on the other hand, HYALECTIN is not useful for wound healing treatments since this fraction does not exhibit cell mobilization activity.

In isolating useful fractions of hyaluronic acid, it is also important to obtain those fractions which do not have inflammatory activity. The Balazs patent noted above teaches that in order to obtain hyaluronic acid fractions without inflammatory activity, fractions having an average molecular weight of more than 750,000 must be utilized exclusively. Thus, Balazs discards the fractions having less than 750,000 average molecular weight as being non-useful because of inflammatory activity. Contrary to the teachings of Balazs, the present applicant has found that the inflammatory activity attributed by Balazs to fractions having an average molecular weight of less than 750,000 is actually due to impurities having an average molecular weight of less than 30,000. Thus, the present invention provides a process which comprises a series of molecular filtration techniques associated with chemical methods by which the inflammatory fraction having a molecular weight of less than 30,000 can be eliminated.

10

20

30

By the processes of facets of the invention, it is possible to obtain useful fractions of hyaluronic acid having no inflammatory activity which, when considered together, constitute a total yield of 80% of the total hyaluronic acid available from the particular starting materials. This 80% yield of the available hyaluronic acid comprises a combined fraction which is a combination of the HYALECTIN and HYALASTINE fractions and which has an average molecular weight of from

\250,000 to \350,000. More specifically, the HYALECTIN fraction is obtained in a yield of 30% of the available HA and the HYALASTINE fraction is obtained in a

yield of 50% of the available HA from the starting tissues. This factor is an important improvement over the process of the Balazs patent discussed above in that the present inventors have discovered that significantly increased amounts of the available hyaluronic acid are pharmaceutically useful. By utilizing only the fraction having an average molecular weight of greater than 750,000, the Balazs process obtains a yield of only 10% of the original hyaluronic acid available from animal organs, and discards

10

20

30

90% of the available hyaluronic acid. Thus, according to the present invention, the usefulness of the total hyaluronic extract has been greatly increased.

A comparison of the relative yields of the extraction of various fractions of hyaluronic acid is presented below in Table 1.

TABLE 1

Type of Hyaluronic Acid	g per 100 g of fresh tissue	8	Reference
Total hyaluronic acid from rooster combs	0.8	100	Swann D.A. 1968, Biochim, Biophys. Acta <u>156</u> , 17-29
HA (Balazs type)	0,08	10	U.S. Patent 4,141,973
HYALECTIN + HYALASTINE	0.6	80	present invention
HYALECTIN	0.2	30	present invention
HYALASTINE	0.4	50	present invention
Inflammatory fraction	0.16	20	present invention

In the accompanying drawings,

Figure 1 is a graph showing the different fractions of hyaluronic acid which have been identified by the present inventors.

Figure 1 graphically shows the different HA fractions which the present applicant has identified. The solid bell-shaped curve of Figure 1 represents the approximate distribution of the HA fractions available from a starting tissue. Area "B" in Figure 1 represents the HA fraction identified by Balazs in U.S. Patent 4,141,973 as being pharmaceutically useful. Areas "A", I and II in Figure I are the fractions identified by the present applicant, area A being the inflammatory fraction having an average molecular weight less than 30,000; area I being the HYALASTINE fraction; and area II being the HYALECTIN fraction. From this graph, it can be seen that the Balazs method discards the large majority of available extractable HA by eliminating the HA fractions having an average molecular weight of less than 750,000. The present invention, on the other hand, permits the pharmaceutical use of a large proportion of available HA since the low molecular weight hyaluronic acid fraction having an average molecular weight of less than 30,000 causes the inflammatory activity which previous investigators have noted with various extracts of HA.

The present applicant has discovered that a large percentage of available HA can, in fact, be utilized for therapeutic purposes if separated according to the teachings of this invention depending upon the particular therapeutic application. While the Balazs patent specifically teaches the use of only 10% of the available HA, the present invention permits the use of 80% of the available HA either in the form of the HYALASTINE fraction for wound healing applications, or in the form of the HYALECTIN fraction for intraocular and intraarticular applications, or in the form of a combined HYALASTINE and HYALECTIN fraction which can also be used for wound healing applications.

The chemical and physical characteristics of the identified fractions have also been investigated by the present applicant, and these characteristics are summarized in Table 2.

Processes Of Preparation

٠ 10

20

Example 1 - Process for obtaining a mixture of HYALASTINE and HYALECTIN fractions without inflammatory activity:

Hen crests, either fresh or frozen (3000 g), are minced in a meat mincer and then carefully homogenized in a mechanical homogenizer. The resulting paste is placed in an AISI 316 stainless steel container or in a glass container with 10 volumes of anhydrous acetone. The entire content is then agitated for 6 hours at a speed of 50 g/minute and left to separate for 12 hours, after which the acetone is syphoned off and discarded.

This extraction process is repeated until the discarded acetone has reached the correct humidity level (Karl-Fischer method).

The resulting substance is then centrifuged and vacuum dried at a suitable temperature for 5-8 hours. With this process, approximately 500-600 g of dry powder is obtained from the hen crests.

300 g of the dry powder is then submitted to an enzymatic digestion process with papain (0.2 g) through a buffered aqueous medium with a phosphate buffer in the presence of a suitable quantity of cysteine hydrochloride. This mixture is then agitated for 24 hours at 60 g/minute at a constant temperature of 60-650C. This whole mass is cooled to 250C adding 60 g of CELDTE , and the agitation is maintained for an additional hour.

TABLE 2 - CHEMICAL AND PHYSICAL CHARACTERISTICS

Fractions	м.м.	Dynamic viscosity at 20%C	Titer in hyaluronic acid of a	Content in proteins as bovine albumin	Content in sulphurated mucopolysac-charides
HYALASTINE					
+					
HYALECTIN	250,000-350,000	100 mP.s. (conc. 1% w/v)	>968a	< 0.58	< 18
HYALASTINE	50,000-100,000	600 mP.s (conc. 5% w/v)	896 <	< 0.5%	< 18
HYALECTIN	500,000-730,000	170 mP.s (conc. 1% w/v)	\$96 <i><</i>	< 0.5%	< 18 ·
•	,				

AValues presented represent the titer in HA after elimination in water. For example, a titer of 96% represents that, after elimination of water, the powder contains 4% impurities and 96% hyaluronic acid.

The resulting mixture is filtered until a clear liquid is obtained. This clear liquid then undergoes molecular ultrafiltration by means of membranes with a molecular exclusion limit of 30,000 to retain on the membrane those molecules with a molecular weight of greater than 30,000. Five to six original volumes are ultrafiltered and, at the same time, distilled water is continually added to the product. The addition of distilled water is suspended and the product is ultrafiltered until it is reduced to one-third of its original volume.

10

The residue liquid is rendered 0.1M by adding sodium chloride and the temperature is brough to 50°C. 45 g of cetylpyridinium chloride is added while the product is being agitated at 60 g/minute. This mixture is agitated for 60 minutes, after which 50 g of CELITE is added. Under agitation the temperature of the product is reduced to 25°C and the precipitate formed is collected by means of centrifugation. The precipitate thus obtained is suspended in a 0.01M solution of sodium chloride (5 liters) containing 0.05% cetylpyridinium chloride. It is agitated for a further 60 minutes at 50°C. The temperature is lowered to 25°C and the precipitate centrifuged.

20

The washing process is then repeated three times and the precipitate finally gathered into containers holding 3 liters of a 0.05M solution of sodium chloride containing 0.05% of cetylpyridinium chloride. This is agitated at 60 g/minute for 60 minutes and maintained at a constant temperature of 25°C for a period of 2 hours. The _____ supernatant is eliminated by means of centrifugation.

30

The procedure is thus repeated several times with a 0.1M sodium chloride solution containing 0.05% of cetylpyridinium chloride. The mixture is centrifuged and the supernatant

discarded. The precipitate is dispersed in a 0.30M sodium chloride solution containing 0.05% of cetylpyridinium chloride (3 1). The mixture is agitated and both the precipitate and the clear liquid are gathered. Extraction is repeated on the precipitate an additional 3 times, each time using 0.5 liters of the same aqueous solution.

Finally, the residue precipitate is eliminated and the clear liquids united in a single container. The temperature of the liquid is increased to 50°C while agitating. The liquid is then brought to 0.23M with sodium chloride. 1 g of cetylpyridinium chloride is added and agitation maintained for 12 hours. The mixture is cooled to 25°C then filtered, first through CELITE packs and then through a filter (14).

10

20

The resultant mixture then undergoes a further molecular ultrafiltration through membranes with a molecular exclusion limit of 30,000, ultrafiltering 3 original volumes with the addition of a 0.33M sodium chloride solution. The addition of the sodium chloride solution is suspended and the volume of the liquid reduced to a quarter of its original volume.

The solution thus concentrated is precipitated under agitation (60 g/minute) at a temperature of 25°C with three volumes of ethanol (95%). The precipitate is collected by centrifugation and the supernatant discarded. The precipitate is dissolved in 1 liter of 0.1M sodium chloride solution and the precipitation procedure is repeated with three volumes of 95% ethanol.

The precipitate is gathered and washed, first with 75% ethanol (three times), then with absolute ethanol (three times) and thirdly with absolute acetone (three times).

The product thus obtained (HYALASTINE + HYALECTIN fraction) has an average molecular weight between 250,000 and 350,000.

The hyaluronic acid yield is equal to 0.6% of the original fresh tissue.

10

30

Example 2 - Process for obtaining the HYALASTINE fraction from the mixture obtained by the method described in Example 1:

The mixture obtained by the process described in Example l is dissolved in pyrogen free distilled water in proportions of 10 mg of product in 1 ml of water. The solution thus obtained undergoes molecular ultrafiltration through membranes with a molecular exclusion limit of 200,000 with a concentration technique and without addition of water on the membrane. During the ultrafiltration process through membranes with an exclusion limit of 200,000, molecules with molecule weight greater than 200,000 will not pass, whereas smaller molecules will pass through the membrane along with the water. During the filtration process no water is added in the compartment above the membrane; therefore, the volume in this compartment will decrease, along with an increase in the concentration of molecules with M.W. over 200,000. It is then ultrafiltered until the volume on the membrane is reduced to 10% of the initial volume. Two volumes of pyrogen free bidistilled water are added and the solution is again ultrafiltered until the volume is reduced to one-third. The operation is repeated another two times.

The solution which passes through the membrane is brought to 1.0M with sodium chloride and then precipitated with four volumes of ethanol at 95%. The precipitate is washed three times with 75% ethanol and then vacuum dried.

The product thus obtained (HYALASTINE fraction) has an average molecular weight between 50,000 and 100,000.

The hyaluronic acid yield is equal to 0.4% of the original fresh tissue.

Example 3 - Process of obtaining HYALECTIN fraction:
The concentrated solution, gathered into a container
from the ultrafiltration membrane with a molecular exclusion
limit of 200,000 described in Example 2, is diluted with
water until a solution containing 5 mg/ml of hyaluronic acid
is obtained, as determined by quantitative analysis based
upon an assay of glucuronic acid.

The solution is brought to 0.1M in sodium chloride and then precipitated with 4 volumes of 95% ethanol. The precipitate is washed three times with 75% ethanol and then vacuum dried.

The product thus obtained (HYALECTIN fraction) has an average molecular weight between 500,000 and 730,000. This corresponds to a specific hyaluronic acid fraction of defined molecular chain length of 2,500 to 3,500 saccharide units with a high degree of purity.

The hyaluronic acid yield is equal to 0.2% of the original fresh tissue.

10

30

Evaluation Of Biological And Pharmaceutical Activity

20 l. Biological activity of cellular mobilization of the hyaluronic acid fractions:

The method, consisting of the determination of the detachment activity of fibroblasts in culture, was used as the method for evaluating the cell mobilization activity of the HA fractions.

Mouse BALB 3T3 cells were grown in Dulbecco's modified Eagle medium supplemented with 10% calf serum, penicillin (250 units/ml) and streptomycin (0.25 mg/ml), and were incubated in humidified 5% CO₂, 95% air at 37°C. For experimental purposes, cells were routinely inoculated in 60-mm diameter plastic tissue culture dishes (6x10⁵ cells/dish).

Confluent monolayers of 3T3 cells were decanted and fresh medium containing 2.0 mg/ml of different fractions of HA were added. At fixed intervals, the cell detachment was observed both microscopically and by counting the mobilized cells in a Coulter Counter.

Detachment assay: To measure detachment kinetics, cells were inoculated into plastic dishes and allowed to grow for 24 hours. After this time, the culture medium was decanted and fresh medium containing 2.0 mg/ml of HA was added. Every 24 hours, two dishes, one each of test culture and of control culture, were decanted and both the cells in the supernatant and the attached cells were counted in a Coulter Counter.

Table 3 reports the results obtained with tests using the fractions obtained in the preparation Examples 1-3 above.

TABLE 3
Results of Mobilization Studies

Fraction	Concentration (mg/ml)	No. of Detached Cells as Compared to Controls	<pre>% Effectiveness (as compared to control)</pre>
Control HYALECTIN		2 x 10 ⁶	
+ .	2	3.5×10^6	75
HYALASTINE			
HYALECTIN	2	2.1 x 10 ⁶	5
HYALASTINE	2	5 x 10 ⁶	150

20

10

The data reported in Table 3 shows that the HYALASTINE fraction exhibits high cell mobilization activity making this fraction useful for wound healing applications. This cell mobilization activity of HYALASTINE will stimulate migration and proliferation of new cells when a pharmaceutical preparation of the fraction is applied to a damaged tissue area.

The HYALECTIN fraction, on the other hand, exhibits very little cell mobilization activity and would not, therefore, be useful for wound healing. HYALECTIN, however, because of its high average molecular weight and inherent viscosity, is useful for ocular and intraarticular injections, and the lack of appreciable cell mobilization activity is an important characteristic of the HYALECTIN fraction making it especially useful for intraocular and intraarticular injections.

2. Biological inflammatory activity of the hyaluronic acid fractions:

For this evaluation, the method of invasive cell count after intraocular administration in rabbits is utilized.

Method

20

10

Five (5) New Zealand or California rabbits, weighing 2 kg and with ascertained perfect vision, are used for this test. The outer eye of the rabbits is checked for inflammatory processes at a macroscopic level and the inner eye is checked by ophthalmoscope. If the ocular fundus is clearly visible and normal, the test may proceed.

The selected animals undergo local anaesthetic by the instillation of a few drops of a suitable sterile anesthetic for ophthalmology; a few drops of atropine in ophthalmological solution are also instilled.

30

The test is carried out in sterile conditions. The ocular globe is made to protrude by means of pressure until

it is possible to inject, through the sclera at 5-6 mm from the limbus, at the center of the vitreal cavity, 100 ALC of the solution, using a 26 G needle. The other eye is taken as a control. Two drops of antibiotic solution are instilled in the treated eye and the animals are then housed in single cages.

After 50-60 hours the test may proceed further. The eyes are checked in the same way as above for the selection of the animals. The animals are sacrificed with an intravenous injection of PENTOTHAL . Then, firstly, the aqueous humor 0.2 ml) is gathered by means of an insulin syringe with a 26 G needle. The ocular globes are then enucleated, freed from all foreign matter, washed in saline, dried with bilbulous paper, and incised and opened in Petri plates, separating the main part of the vitreous humor and gathering it with a sterile syringe (0.7 ml). The vitreous humor is placed in small polyethylene test tubes and 50 u.f. hyaluronidase (100 U NF/ml) is added. The mixture is then kept at a temperature of 37°C for 3 hours in order to render the solution less viscous.

20

.10

A leukocyte count is carried out under a microscope by phase contrast (120 x) in a Burker chamber. A series of counts is effected on each sample, calculating the average values and expressing the result as the number of leukocytes per mm^3 .

The test is considered positive when:

- 1) the eyes examined show no signs of suffering, and
- 2) the average number of leukocytes from at least 4 of the 5 treated eyes does not exceed 200 per mm³ and the average number of leukocytes from each control eye does not exceed 50 per mm³.

30

Table 4 reports the results obtained from this evaluation using the HA fractions obtained in preparation Examples 1-3 discussed above.

TABLE 4

Results of Inflammatory Activity Studies

	Fraction	No. of Invasive Cells	
	Control	25	
	HYALASTINE + HYALECTIN	32	
	HYALASTINE	20	
	HYALECTIN	22	
10	Inflammatory Fraction (Avg. MW of 30,000)	150	
	Total Hyaluronic Acid from Rooster Combs (RF. Swann D.A. 1968, B.B.A. 156, 17-29)	120	

The results reported in Table 4 show that the HYALASTINE and HYALECTIN fractions exhibit no inflammatory activity above that for the control, and the combined HYALASTINE and HYALECTIN fraction showed only a negligible increase in inflammatory activity over the control. Accordingly, the HYALASTINE and HYALECTIN fractions are pharmaceutically useful without exhibiting undesirable inflammatory side effects. These results also further confirm the applicant's discovery that it is the HA fraction having a low average molecular weight of less than 30,000 which is responsible for the inflammatory activity of HA preparations. Hyaluronic acid from rooster combs, prepared according to the method described in the literature by Swann (Swann D.A. 1968, B.B.A. 156, 17-29), shows a remarkable inflammatory activity.

ŻC

It has thus been shown that the HYALASTINE fraction having an average molecular weight of 50,000 to 100,000 exhibits high cell mobilization activity and is, therefore, useful in wound healing applications without exhibiting undesirable inflammatory reactions. The HYALECTIN fraction, having an average molecular weight of 500,000 to 730,000, has been shown to be useful for ocular and intraarticular injection due to its high molecular weight and inherent viscosity, and, at the same time, does not stimulate cell mobilization activity or inflammatory reactions which are undesirable side effects to be avoided in these pharmaceutical applications.

More specifically, the HYALASTINE fraction has been found to be useful as a wound healing preparation because of the following characteristics.

10

20

30

- The preparation promotes a remarkably shortened healing time, as compared to conventional therapy, with rapid clearing of the affected area, regularization of ulcer edges, vigorous development of granulation tissue, activation of cellular migration of macrophages and fibroblasts and early epithelization.
- 2. The preparation promotes increased amenability to reconstructive surgery in the more severe cases.
- 3. The absence of keloid or retracting scar formation, with final reshaping of cicatricial tissue yielding good cosmetic and functional results.

The HYALASTINE preparation has been found to be useful for the treatment of various wounds including decubitus sores (bed sores), trophic ulcers, burns, indolent wounds, post-traumatic ulcers, varicose and postphlebitic ulcers from venous blood stains, radionecroses, skin lesions, skin grafts

and skin lesions due to herpes simplex. For these wound healing treatments, the HYALASTINE preparation, or the sodium salt thereof, can be administered in various methods, such as by gauze pads, cream, spray or ampoules for intradermal injection. For the topical applications as a cream or on a gauze pad, the HYALASTINE is preferably combined with an emulsifying agent, which absorbs the exudate from the exposed area while affording excellent diffusion of hyaluronic acid, and a water-dispersible excipient so that the wound dressing is easily removed.

10

20

30

The HYALECTIN fraction has been found to be particularly useful for the treatment of horses, particularly race horses, suffering from joint disorders and diseases caused by acute or chronic trauma, infections or repeated intraarticular corticosteroid injections. Specific examples of disorders treatable with HYALECTIN are osteoarthroses with or without inflammatory signs, acute or chronic synoritis, degenerative processes in articular cartilage, and dry joint disease. most frequent symptoms of these disorders are generally pain, impaired joint function, and reduced joint flexion. The HYALECTIN fraction of the invention has been found to promote marked reduction of the healing time for such affected horses as compared with conventional therapy, to promote early and lasting improvement of joint function and to reduce pain and lameness. These clinically advantageous effects are believed to be promoted by a normalization of the viscoelasticity of the synovial fluid and by activation of tissue repair processes in the articular cartilages.

Moreover, all the above advantageous effects are promoted by the HYALECTIN fraction in the absence of local and/or systemic toxic effects. Repeated administration of HYALECTIN produces no evidence of allergic reactions nor any adverse or lasting effects.

Pharmaceutical Preparations

The above disclosure has shown that the HYALASTINE and HYALECTIN fractions have good activity for pharmaceutical applications. The following examples are presented for exemplary purposes only to describe possible pharmaceutical preparations for actual in vivo administration of the HA fractions.

A. Preparations for Wound Healing

10	Example 1:	ampoules for intradermal injectio each ampoule contains: -Hyalastine sodium salt -Sodium Chloride -Water for injection q.s.a	mg	
	Example 2:	ampoules for intradermal injection each ampoule contains: -Hyalastine potassium salt -Sodium Chloride -Water for injection q.s.a	mg	
20	Example 3:	spray-bottle for topical applicate each bottle contains: -Hyalastine sodium salt -Sodium Chloride -Water for injection q.s.a.	mg	20 80 10
į	Example 4:	spray-bottle for topical applicate each bottle contains: -Hyalastine potassium salt -Mannitol -Water for injection q.s.a.	mg mg	30
•	Example 5:	cream for topical application - each tube of cream contains: -Hyalastine potassium salt -Polyethyleneglycol mono-	mg	25
30	\	stearate 400 - cerror (decyl ester of oleic acid) - LANETTE SX (cetyl-stearyl alcohol + lauryl sulfate 9:1)	mg mg	1000500150

	·		-Glycerol -Sorbitol -Na-dehydroacetate -p-oxymethylbenzoate -p-oxypropylbenzoate -redistilled water	q.s.a.	mg mg mg	200 150 10 7.5 5
	Example	6:	cream for topical applicate each tube of cream contains -Hyalastine sodium salt -Paraffin jelly		mg mg	30 3
-			-Polyethyleneglycol mono- stearate 400 -CETIOL (decyl ester of o	leic	mg	1000
• •			acid)		mg	500 .
10			-IANETTE SX (cetyl-steary alcohol + lauryl sulfate -Glycerol -Sorbitol		mg mg	150 200 150
			-Na-dehydroacetate		mg	10
	•		<pre>-p-oxymethylbenzoate -p-oxypropylbenzoate</pre>		mg mg	7.5 5
			-redistilled water	q.s.a.	ğ	10
	Example	7:	medicated gauze pads for each gauze-pad measuring -Hyalastine sodium salt -Glycerol -Polyethyleneglycol -redistilled water			
20		_			-	
	Example	8:	medicated gauze-pads for each gauze-pad measuring -Hyalastine potassium sal -Paraffin jelly -Glycerol -Polyethyleneglycol -redistilled water	15x15 cm		
	 Example	9:	dry powder for wound heal		icati	on -
			each gram of dry powder co- -Hyalastine sodium salt	ontains:	mg	10
	•		-Mannitol -Glycine		g g	0.75 0.24
30			1		ד	0.44

	В.	Preparations	for Intraocular Use		•
		Example 10:	<pre>l-ml vials - each vial contains:</pre>		·
			-Hyalectin sodium salt	mg	10
			-Sodium Chloride	mg	8
			-Monobasic sodium phosphate	-	
			2H ₂ O	mg	.0,25
			-Dibasic sodium phosphate	•	•
			12H ₂ O	mg	3
			-Water for injection q.s.a.	=	ī
			Total and an arrangement of the second of th		-
10		Example 11:	5-ml vials -		
		•	each vial contains:		
			-Hyalectin potassium salt	mg	60
			-Mannitol	mg	50
			-Monobasic sodium phosphate	-	
			2H ₂ O	mg ·	1.25
			-Dibasic sodium phosphate		
			12H ₂ O	mq	15
		•	-water for injection q.s.a.	-	5
					-
		Example 12:	preloaded syringes -		
20			each syringe contains:		
~~			-Hyalectin sodium salt	mg	40
•			-Sodium Chloride	mg	16
			-Monobasic sodium phosphate	5	
			2H ₂ O	mg	0.8
		•	-Dibasic sodium phosphate		•••
		5	12H ₂ O	mq	8.16
			-Water for injection q.s.a.		2
			mader ret engeeten quant	•	_
	c.	Preparations	for Intra-Articular Use	;	
		Example 13:	2-ml vials -		
30		Example 13.	each vial contains:		
30		•	-Hyalectin sodium salt	mg.	40
			-Sodium Chloride	mg '	16
			-Water for injection q.s.a.		2
			-water for injection q.s.a.	1117	2 .
		Example 14:	4-ml vials -		
		Example 14:	each vial contains:		•
			-Hyalectin potassium salt	ma	60
			-Mannitol	mg	35
		•	-Glycine	mg mg	10
				mg ml	4
			-Water for Injection q.s.a.	ml .	72

Example 15	<pre>: preloaded syringes - each syringe contains:</pre>	•	•
	-Hyalectin sodium salt	mg	25
	-Sodium Chloride	mg	12
	-Mannitol	~mg	10
	-Monobasic sodium phosphate		
	2H ₂ O	mg	0.5
	-Dibasic sodium phosphate		
	12H ₂ O	mg	6
•	-Water for injection q.s.a	. ml	2

Although the above-preparations have been described for exemplary purposes, it will be appreciated that other pharmaceutical formulations could be prepared by combining the HYALASTINE and HYALECTIN fractions discovered by the inventors, or the potassium or sodium salts thereof, with other pharmaceutically acceptable carriers, diluents, or excipients and at various dosages depending upon the particular use for the formulation.

10

20

For wound healing uses, the preparations of the HYALAS-TINE fraction are applied to the affected skin areas in one of the dosage forms discussed above, that is, either as a cream, a spray, on a gauze-pad, as a dry powder or as an intradermal injection.

For intraarticular uses, the preparations of the HYALECTIN are generally administered at a dosage rate of 2 ml per joint taken either from a prepared vial or a preloaded syringe as described above.

In an additional study, the capacity and efficiency of hyaluronic acid as a vehicle for various molecules has been investigated, in particular, use as a vehicle for opthalmic drugs, guaranteeing perfect tolerability and compatibility (i.e., absence of sensitization phenomena) with the corneal epithelium. Hyaluronic acid is considered of particular interest as an ophthalmic vehicle. As discussed previously, HA is a glycosaminoglycan present in various connective tissues and biological liquids (e.g. the synovial fluid

and in particular the vitreous humor) where, because of its chemical and physical nature and its striking visco-elastic characteristics, it plays a structural and biological role of fundamental importance.

Thus, a study was conducted to investigate the use of HA fractions having different molecular weights, particularly the hyalastine and hyalectin fractions, and a mixture of the same, for the preparation of different pharmaceutical forms, e.g. collyrium, gel, cream, inserts or dry powders. Therefore, opthalmic durgs of different types were studied in order to obtain a broad understanding of the potential use of this biological polymer in its different fractions as a vehicle.

10

20

30

The experiments reported hereafter were aimed at determining whether formulations containing hyaluronic acid as an excipient are capable of enhancing the bioavailability of vehicled drugs or producing a synergistic effect in combination with the vehicled drugs, particularly with drugs having ophthalmic activity or utility.

These potential capacities of HA as a vehicle were investigated in the rabbit eye with four ophthalmic drugs of different types and actions, in particular, pilocarpine nitrate, triamcinolone, epidermal growth factor (EGF) and an antibiotic e.g. streptomycin and gentamicine. All of these drugs are known to have miotic, anti-inflammatory, healing and anti-microbial efficiency. Moreover evaluation of the activity of the antibiotic streptomycin, vehicled in hyaluronic acid, is very important because it is one of the most widely used antibiotics in ocular infections.

The experimental models studied and the experiments effected were as follows:

- miotic activity of pilocarpine nitrate, vehicled in hyaluronic acid in rabbit eye;
- 2) anti-inflammatory activity of triamcinolone, vehicled in hyaluronic acid in the model of dextran-induced inflammation in rabbit eye;
- 3) healing activity of epidermal growth factor (EGF) vehicled in hyaluronic acid in a model of epithelial lesion of rabbit cornea.
- 4) antimicrobial activity of streptomycin vehicled in hyaluronic acid against <u>Bacillus subtilis</u> 6633 in agar plates.
- I. Miotic Activity of Pilocarpine Nitrate Vehicled In Hyaluronic Acid

Materials

10

The following materials were used as excipients of pilocarpine for the various pilocarpine nitrate formulations:

- -- hyaluronic acid sodium salt, hyalastine fraction, (m.w., approximately 100,000), at a concentration of 10 mg/ml and 20 mg/ml;
- -- hyaluronic acid sodium salt, hyalectin fraction (m.w. 500,000 730,000), at a concentration of 10 mg/ml and 20 mg/ml;
 - -- 5% polyvinyl alcohol as a comparative ophthalmic excipient.

Various 2% formulations (collyrium or gel) of pilocarpine nitrate were prepared and vehicled by adding the two different fractions of HA sodium salt at a concentration of 10 and 20 mg/ml. The following solutions were prepared:

Formulation 1 - saline with pilocarpine nitrate ($PiNO_3$) (2%), used as reference.

Formulation 2 - solution of PiNO₃ (2%) vehicled in 5% polyvinyl alcohol (used as reference).

Formulation 3 - solution of $PiNO_3$ (2%) vehicled in hyalastine fraction sodium salt (10 mg/ml).

Formulation 4 - solution of $PiNO_3$ (2%) vehicled in hyalastine fraction sodium salt (20 mg/ml).

Formulation 5 - solution of $PiNO_3$ (2%) vehicled in hyalectin fraction sodium salt (10 mg/ml).

Formulation 6 - solution of $PiNO_3$ (2%) vehicled in hyalectin fraction sodium salt (20 mg/ml). Method

Albino New Zealand rabbits were used (2 - 2.5 kg). The formulation to be tested was instilled in one eye by microsyringe (10 1); the other eye served as a reference. The diameter of the pupil was measured in all cases at suitable time intervals. Each solution was tested on at least 8 rabbits. Each eye was treated not more than three times and a rest period of at least a week was observed between each treatment.

Parameters Measured

10

20

The pupil diameters were measured at various intervals in order to determine the miotic activity curve in time. The following activity parameters were subsequently calculated from the miosis/time graphs:

I max = maximum difference in pupil diameter between the treated eye and the reference.

Peak time = time taken to reach Imax.

Duration = time taken to restore basal conditions. Plateau = period of absolute miotic activity.

AUC = area under miosis/time curve.

Results

10

The results of the tests are reported in Table 5. It can be seen from the data for the various parameters determined from the miotic activity time curve for all the solutions tested that the addition of hyaluronic acid to a 2% pilocarpine nitrate solution gives rise to an increase in miotic activity of the drug. In fact, the bioavailability of the drug may be as much as 2.7 times greater than that of the aqueous solution containing 2% pilocarpine nitrate (Formulation 1).

It should also be noted that there is a statistically significant increase in activity when the hyalectin fraction of hyaluronic acid both at 10 and 20 mg/ml is used as a vehicle (Formulations 5-6), in contrast to the pilocarpine nitrate solution vehicled in polyvinyl alcohol (Formulation 2).

The use of hyaluronic acid as a vehicle is particularly interesting because the miotic activity of pilocarpine nitrate lasts longer when it is vehicled with this substance. That is, for the hyaluronic acid containing formulations the time taken to restore pupil diameter to basal conditions is up to 190 minutes (Formulation 6) as compared to 110 minutes for pilocarpine in saline alone (Formulation 1).

II. Anti-Inflammatory Activity Of Triamcinolone Vehicled In Hyaluronic Acid

Materials

The following were used:

- -- solution of hyaluronic acid sodium salt-hyalectin fraction, m.w. between 500,000 and 730,000, 10 mg/ml in saline;
- -- solution of triamcinolone (10% in saline).

10 Method

The experiments were carried out on male New Zealand rabbits (average weight 1.6 kg). After an adaptation period of 5 days, intraocular inflammation was induced in the rabbits by intraocular injection of dextran (10%, 0.1 ml). The administration was effected in both eyes under local anaesthetic with 4% NOVASINA inserting the needle of the syringe by 4 mm into the anterior chamber, at a distance of 2 mm from the limbus of the cornea. The test was conducted on 10 animals.

Table 5: Biological Activity of Ophthalmic Formulations Containing Pilocarpine-Nitrate Vehicled by Hyaluronic Acid^a

į

Formu- lation	Vehicle	Imax' mm (+ LF 95%)	Peak time (minutes)	Duration (minutes)	Plateau (minutes)	Duration Plateau AUC, cm ² Relative (minutes) (minutes) (+ LF 95%) AUC	Rela
~	saline	1.93 ± 0.35	20	110	.	117 ± 28	`
7	5% polyvinyl alcohol 2.33 ± 0.28	2.33 ± 0.28	20	140	1	192 ± 32	
m	hyalastine (10 mg/ml) 2.50 \pm 0.42	2.50 ± 0.42	20	120	ì	240 + 40	
₩.	hyalastine (20 mg/ml) 2.58 \pm 0.38	2.58 ± 0.38	30	150	1	208 ± 41	
ر ا	hyalectin (10 mg/ml)	2.50 ± 0.38	15	170	1 .	242 + 48	
ø	hyalectin (20 mg/ml)	(20 mg/ml) 2.70 + 0.38	20	190	45	320 + 45	

a Reported values represent a mean value for 8 runs.

Treatment

Treatment was effected in each animal both in the right and left eyes, by instillation of 3 drops 3 times a day for 6 days in all, of the following:

- a solution of triamcinolone (10% in saline) in the left eye (LE);
- a solution of hyaluronic acid sodium salt, hyalectin fraction, (10 mg/ml) + triamcinolone (10%) in the right eye (RE).

10 Parameters

The anti-inflammatory effect on the phlogistic reaction induced by dextran was evaluated by observing the eye with a slit lamp at the following intervals: 0, 1 hr, 3 hr, 24 hr, 48 hr, 3 days, 4 days, 5 days and 6 days.

At the intervals, the eye examination evaluated the following observations:

- the state of the cornea and conjunctiva for the possible presence of hypermia, edema, and especially observation of the iris which is normally sensitive to phlogistic processes after intraocular injection of inflammatory agents;
- the Tyndall effect, in which the presence of more or less intense opacity ("nubecula") is indicative of the presence of corpusculating (inflammatory) elements in the anterior chamber.

The result of the observation was expressed in terms of subjective scoring (from 0 to 3) related to the gradualness of the effect noted.

20

Results

10

20

It can be seen from the results as reported in Table 6 that administration of triamcinolone has an anti-inflammatory effect on the iris and causes the disappearance of opacity (Tyndall effect) in the anterior chamber. The inflammatory process which is evident from the 1st-3rd hour until the 3rd to 4th day progressively decreases until almost normal conditions are restored, with perfect limpidness of the eye by the 6th day. On the other hand, administration of hyaluronic acid sodium salt, hyalectin fraction, together with triamcinolone reduces intraocular inflammation observed at the times discussed above relating to administration of triamcinolone alone. That is, the phlogistic process in the iris and the opacity in the anterior chamber is seen to have decreased by the 24th hour, with progressive reduction at 48 hours and with total absence of inflammatory reaction from the 4th day on.

In the conjunctiva and the cornea, essentially no notable reactions were observed after intraocular injection of dextran.

Thus, the administration of triamcinolone, together with the hyaluronic acid fraction, resulted in enhanced activity of the drug as evidenced by the more rapid recovery of the rabbit eye. -32÷

EFFECT OF THE COMBINATION OF HYALURONIC ACID AND TRIAMCINOLONE ON INTRAOCULAR INFLAMMATION INDUCED BY DEXTRAN

Observation Interval

	0	lhour	3hours	24hours	48hours	3days	4days	5days	6days
				Evaluat	Evaluated Score				
	LE RE	LE RE	LE RE	LE RE	LE RE	LE RE	LE RE	LE RE	LE RE
Conjunctiva	0.0 0.0	0.2 0.0	0.0 0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0
Cornea	0.0 0.0	1.0 0.2	0.0 0.7	0.1 0.0	0.1 0.0 0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0
Tyndall	0.0 0.0	1.0 1.2	3.0 3.0	3.0 2.1 3.0 1.2	3.0 1.2	3.0 0.2	2.2 0.0	1.2 0.0	0.4 0.0
Iris	0.0 0.0	0.5 0.7	2.7 2.7	3.0 2.5 3.0 1.2	3.0 1.2	3.0 0.4	3.0 0.4 2.4 0.0	1.5 0.0	0.5 0.0
	•								

LE = Left eye, treated with triamcinolone.

RE = Right eye, treated with tiamcinolone and hyalectin.

agach value is the mean of seven observations in a total of seven animals, and expressed in terms of subjective scoring between 0 and 3, in relation to the gradualness of the effect observed.

III. <u>Healing Activity of EGF Vehicled in Hyaluronic Acid</u> Materials

The following were used:

Formulation A - EGF (Epidermal growth factor), dissolved in saline (0.5 mg/5 ml)

Formulation B - hyaluronic acid sodium salt, hyalastine fraction, (m.w. approximately 100,000) dissolved in saline (10 mg/ml)

Method

The experiments were carried out on male albino New Zealand rabbits (average weight 1.8 kg). The animals, after a period of adaptation of about 5 days, underwent epithelial lesion of the cornea in suitable conditions of local anaesthetic with NOVASINA '4%). The lesion consisted of a monocular scarification of a circular area in the optic zone effected by a concave glass cylinder (Ø 3mm) with a sharp edge.

Treatment

Group

The animals were subdivided into groups, each group con-20 sisting of 5 animals, and subjected to pharmacological treatment by conjunctival instillation as follows:

Treatment

	Group 1 (control)	Saline
	Group 2	EGF solution (Formulation A)
•	Group 3	Solution of hyaluronic acid sodium salt, hyalastine fraction, + EGF solution - combination of Formulation A + Formulation B at 1:1 ratio to make Formulation C

Treatment was effected on the right eye (RE) by conjunctival instillation of 2 drops every 8 hours for 3 total administrations.

Parameters

Healing of the corneal epithelium was evaluated by observation of the eye and photographic documentation with a slit lamp at various intervals after scarification: 0, 8 hours, 16 hours, 24 hours, 32 hours, 40 hours, and 48 hours. Results

Ophthalmological examination 1 as reported in Table 7, revealed that in the controls (Group 1) complete healing was achieved (5/5 animals) 48 hours after lesion. In the animals treated with EGF (Group 2) the healing process was apparent as early as 24 hours after scarification with considerable efficacy (4/5 animals). In the animals treated with the Formulation C comprising hyaluronic acid sodium salt, hyalasline fraction, + EGF (Group 3) the healing process was complete in all the animals (5/5) as early as 16 hours after scarification.

These results show that utilization of the hyalastine hyaluronic acid fraction as a vehicle for EGF enhances the healing process by promoting more rapid effective healing of corneal lesions.

Table 7
HEALING OF LESIONS IN THE CORNEAL EPITHELIUM

Group	Treatment	Hours	after	scari	tication	
		0	8	16	24	48
1 .	Saline	+	+	+	+	
		+	+	+		_
	•	+	+	+	. + +	_
		+	+	+	+	. —
	,	+	+	+	+ 1	-
2	EGF (Formulation A)	+	+	+	-	-
•		+	+	+	-	-
		+	+	+	-	-
		+	+	+ .	+ .	-
		+	+	+	-	- :
3	Hyaluronic acid + EGF (Formula-	+	+	_		_
	+ EGF (Formula- tion C)	+	+	- !	-	_
		+	+ .	-		_
		+ .	+	_	-	
		т .	T	-	-	-

^{+ =} unhealed eye

^{- =} healed eye

IV. Antimicrobial Activity of Gentamicine Vehicled in Hyaluronic Acid

Materials

The following materials were used:

- -- Gentamicine dissolved in saline (50 mg/ml)
- -- Hyaluronic acid sodium salt, hyalectin fraction (2 mg/ml)

Method

20

Septic phlogosis was caused in both eyes of 11 rabbits by intraocular injection of a titered suspension of <u>Pseudomonas aeruginosa</u> (0.1 ml). In those rabbits showing septic phlogosis, hyaluronic acid, hyalectin fraction, in combination with gentamicine was administered by instillation in the right eye and gentamicine in a buffered saline vehicle was administered in the left eye. The treatment (3 drops every 6 hours) was begun immediately after injection of the infecting agent and was continued until the infection had disappeared. The rabbits' eyes were observed every day under a slit lamp. Results

Treatment with a combination of gentamicine with hyaluronic acid resulted in a faster disappearance of the septic infection as compared to administration of the antibiotic alone. This conclusion is clear from the data presented in Table 8.

Table 8

EFFECT OF GENTAMICINE VEHICLED IN HYALURONIC ACID
HYALECTINE FRACTION, ON INTRAOCULAR SEPTIC PHLOGOSIS

Treatment	Days from Start of Phlogosis								
	1	2	3	4	, 5	6	7		
Gentamicine + Buffer Saline Vehicle	0.0	0.0	0.0	0.0	0.0	36.3	100		
Gentamicine + Hyaluronic Acid Hyalectine Fraction	0.0	0.0	9.0+	27,2+	72.7+	100	100		

Values are expressed as percentages (number of eyes cured of phlogosis by the number of eyes treated).

^{+ =} Significant difference vs buffer vehicle (less than 0.05, Fisher exact T-Test)

Additional samples, although not limitive, of ophthalmic drugs which can be vehicled with HA fractions according to the invention are as follows:

antibiotics:

chloramphenicol

neomycin aureomycin

myxin and polymyxin

bacitracin mycetins

10

hormones:

nandrolone and nandrolone sulfate

anesthetics (local):

henoxinate and the hydrochloride

thereof

antiviral:

iododeoxyuridine
iododeoxycytidine

anti-inflammatories:

dexamethasone and the phosphate

thereof

vasopressors and

vasocontrictors:

synephrine and neosynephrine

On the basis of the results obtained from the experiments discussed above, it can be concluded that solutions of hyaluronic acid sodium salt (in both the hyalastine and hyalectin fractions) can be used as a vehicle for ophthalmic drugs and proves to be efficient as such for various types of drugs having differing biological actions. For example, drugs including anti-glaucoma agents e.g. pilocarpine nitrate, anti-allergic and anti-inflammatory agents triamcinolone, tissue healing and cell proliferation promoting agents for promoting healing of eye tissue such as EGF, and antibiotics e.g. streptomycin and gentamicine, whose miotic, anti-inflammatory, healing and antimicrobial activities respectively are reported, can all be administered effectively utilizing HA as a vehicle.

10

20

The formulations of ophthalmic drugs vehicled in hyaluronic acid fractions with various molecular weights prove to be perfectly tolerated by the host, and compatible with the corneal epithelium without, therefore, giving rise to sensitization phenomena.

It is also possible from the data to observe how this biological product, hyaluronic acid, is an efficient vehicle, capable of enhancing the in vivo bioavailability of vehicled drugs, strengthening the pharmacological activity of such drugs. The use of hyaluronic acid fractions as a drug vehicle particularly results in:

- an increase in the miotic activity of pilocarpine nitrate while prolonging the activity time of the drug;
- an increase in the anti-inflammatory activity of triamcinclone on intraocular inflammation induced by dextran, with a regression of the phlogistic process in shorter times as compared to those obtained with triamcinclone alone;
- an increase in the protective action of epidermal growth factor (EGF) on superficial lesions in the cornea with obvious synergism and reduction in healing times as compared to recovery times with EGF alone; and
- an increase in the in vivo biological activity of antibiotics, such as gentamicine.

The results obtained by using this biological polymer, hyaluronic acid, as a vehicle for drugs with such varied natures and actions, allows for the extrapolation of its potential as a vehicle for numerous other ophthalmic drugs.

Reported below are various examples of different formulations of ophthalmic drugs which may be in the form of powders, collyrium, gel, cream, or inserts, in which hyaluronic acid in its different fractions, hyalastine and hyalectin, is the only excipient used:

Example 1:

10

20

30

- a collyrium which may be used as "artificial tears", containing:
- hyaluronic acid sodium salt hyalectin fraction 10 mg
- saline buffered with phosphate pH 7.6 M 10 ml Example 2:
- a collyrium which may be used as "artificial tears" containing:
 - hyaluronic acid sodium salt hyalectin fraction 20 mg
 - saline buffered with phosphate pH 7.6M
 10 mg

Example 3:

- a gel containing EGF in which 100 g contain:
- hyaluronic acid sodium salt hyalastine fraction 55 g
- hyaluronic acid sodium salt hyalectin fraction 30 g
- EGF 0.5g
- twice distilled water 23.5g

Example 4:

- a 100 mg insert with pilocarpine nitrate containing:
- hyaluronic acid sodium salt hyalastine fraction 100 mg
- pilocarpine nitrate 2 mg

Example 5:

10

20

- a powder form for topical application containing streptomycin. 100 g of powder contain:
- hyaluronic acid sodium salt hyalastine fraction 70 g
- hyaluronic acid sodium salt hyalectin fraction 28.5 g
- streptomycin 1.5 g

Although the above-preparations have been described for exemplary purposes, it will be appreciated that the pharmaceutical formulations could be prepared by combining the hyaluronic fractions, particularly the hyalectin or hyalastine fractions or the combined hyalectin/hyalastine fraction, or the potassium or sodium salts thereof, with other active drugs, and at various dosages depending upon the particular use for the formulation.

Hyaluronic acid, particularly in the substantially pure hyalectin and hyalastine fractions, has, therefore, been shown to be an effective vehicle or excipient for use in combination with various drugs having ophthalmic utility or activity. Pharmaceutical compositions containing the HA fractions as the drug vehicle are particularly useful because the HA fractions exhibit a high level of tolerability to the eye and a high compatibility with the corneal epithelium.

Use of the HA fractions, moreover, provides a means for actually enhancing the in vivo biological activity of ophthalmic drugs. The use of the particular hyalectin and hyalastine HA fractions is further useful and important because these fractions, when administered in the eye, do not exhibit undesirable inflammatory side reactions.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A process for preparing a substantially pure, non-inflammatory, hyaluronic acid fraction comprising:

dehydrating tissue containing an available amount of hyaluronic acid;

subjecting the resulting dehydrated tissue to enzymatic digestion; and

subjecting the resulting mixture to molecular filtration to obtain a hyaluronic acid fraction having an average molecular weight of from 50,000 to

350,000 or

100,000, from 250,000 to from 500,000 to 730,000.

2. A process for preparing a substantially pure, non-inflammatory hyaluronic acid fraction comprising:

dehydration of tissue available for extraction of hyaluronic acid;

subjecting the resulting substance to enzymatic digestion;

subjecting the resulting mixture to molecular filtration with a membrane having a molecular weight exclusion limit of 30,000 to exclude molecules having a molecular weight of greater than 30,000; and

1205031

collecting the mixture retained by said membrane; thereby obtaining a first hyaluronic acid fraction product having an average molecular weight of from 250,000 to 350,000.

- 3. A process for preparing a substantially pure, non-inflammatory hyaluronic acid fraction as claimed in claim 2, which comprises: subjecting said first hyaluronic fraction to further molecular ultra-filtration with a membrane having a molecular weight exclusion limit of 200,000 to exclude molecules having a molecular weight greater than 200,000; continuing ultra-filtration until the volume of the mixture being subjected to ultra-filtration is reduced to 10% of the initial volume; and collecting the mixture which passes through the membrane; thereby to obtain a second hyaluronic fraction product having an average molecular weight of from 50,000 to 100,000.
- 4. A process for preparing a substantially pure, non-inflammatory hyaluronic acid fraction comprising: collecting the mixture retained on the membrane after the ultra-filtration step with a membrane having a molecular weight exclusion limit of 200,000 as claimed in claim 3; thereby obtaining a third hyaluronic acid fraction product having an average molecular weight of from 500,000 to 730,000.
- 5. A substantially pure, non-inflammatory hyaluronic acid fraction having an average molecular weight of between 30,000 and 730,000, or the potassium or sodium salt thereof, whenever prepared by the process of claim 1 or by its obvious chemical equivalent.
- 6. A substantially pure, non-inflammatory hyaluronic acid fraction as claimed in claim 5, having an average molecular weight of between 250,000 and 350,000 or the potassium or sodium salt thereof, whenever prepared by the process of claim 2 or by its obvious chemical equivalent.

1205031

- 7. A substantially pure, non-inflammatory hyaluronic acid fraction as claimed in claim 5, having an average molecular weight of between 50,000 and 100,000 or the potassium or sodium salt thereof, whenever prepared by the process of claim 3 or by its obvious chemical equivalent.
- 8. A substantially pure, non-inflammatory hyaluronic acid fraction as claimed in claim 5, having an average molecular weight of between 500,000 and 730,000 or the potassium or sodium salt thereof, whenever prepared by the process of claim 4 or by its obvious chemical equivalent.



465231

Abstract of the Disclosure

Two pharmaceutically useful fractions of hyaluronic acid are obtained comprising a first fraction with a molecular weight between 50,000 and 100,000 which is useful for wound healing, and a second fraction having a molecular weight between 500,000 and 730,000 which is useful for intraocular and intraarticular injections. The fractions of hyaluronic acid are further useful as vehicles for opthalmic drugs, providing formulations compatible with the corneal epithelium and enhancing in vivo activity of such drugs.

10